

The Development of the New High Temperature Resistance Profile Control Agent which is Compound with Inorganic Particles and Gel

Cuiting Zhang, Changfu Li

Panjin Vocational and Technical College, Panjin, 124000, China

Abstract: At present, High temperature profile control technology has become the key technology to improving recovery efficiency, management of steam channeling in thermal recovery. the particle of regular application is dosage big, poor injection and easy to cause the rigid block, Gel and foam profile control agent is poor stability, low intensity and short validity period. For the above problems, Developed a new type of high temperature resistance particle - gel complex profile control system through the theoretical analysis and the ratio optimization of indoor experiment and evaluate its performance. The formula of the system: 0.03% Coagulant+ 2.2% cross-linking agent I +1.8%cross-linking agent II+6% modified high temperature resistance main agent +0.7% new type inorganic particles +0.5% suspending agent. At least 280°C of heat-resistant, two-fluid process injection, injection performance is good, the plugging rate is more than 99.05%, scouring resistance and it has good thermal stability. This study provide a new direction for the thermal profile and theoretical basis for profile control construction.

Keywords: Thermal recovery; Steam channeling; Compound; Profile control agent; Two-fluid process.

1. Introduction

High temperature profile control medium at home and abroad mainly for the high temperature resistant foam, gel, inorganic particles. Under the condition of meet the requirements of heat resistance, foam profile control agent is poor stability, the validity of gel profile control agent is short, the particle profile control agent is easy to cause the rigid block and poor injection, and then damage the formation[1,2]. the profile control agent is inefficiency when used alone, This project adopts the modification technology to improve the heat-resistant ability of the traditional high temperature resistant main agent, With coagulant and two types of cross-linking agent to form a space mesh quadripolymer gel and Used with new type of high temperature resistance inorganic particle. Further improve the temperature resistance, erosion resistance of the profile control agent. Gels and the particle which is fell off has the effect of deep migration, it is an ideal profile control agent. this study provide reference for other high-temperature profile control technology research and has a guiding significance for site construction applications.

2. The Mechanism of the Complex System

The system is compound with gel and particles, using the modified high temperature resistant main agent, the main agent with coagulant and two types of cross-linking agent make a quadripolymer reaction, Generated the gel system with dense interpenetrating space network structure. the new type of high temperature resistant inorganic particles suspend in the gel solution uniformly and support each other with gel for improve the temperature resistance, erosion resistance of the profile control agent. Inorganic particles are the tiny particles, they have the effect of deep migration with the gel ball which is cut into small pieces.

3. The Development of high Temperature Resistant Gel Main Agent

65% concentrated nitric acid is used in experiments by a certain percentage which make modification reaction with the traditional high-temperature main agent, On the basis of the original molecules, increasing nitrocellulose to improve heat resistance performance. By contrast gelling colloidal temperature resistance, screening and optimizing Formulation the best of the main agent[3]. High temperature resistant test results show that when the solid-liquid ratio is 1:6, it has the least amount of dehydration at high temperatures after the Generated main agent gelled, And still keep high strength and toughness.

the PH of the preparation of modified high temperature resistant main agent product is between 2 ~ 3 in the end, the PH of aqueous solution value is neutral, when the mass fraction is greater than or equal to 14%, the solubility is saturated and is dark red, the generated gel meet the requirements of high temperature resistant performance under the high temperature of 280°C [4].

4. The Experiments of Ratio Optimization

Experimental drug: Coagulant, Modified high temperature resistant main agent, cross-linking agent I, cross-linking II, PH adjusting agent, formation water.
Experiment instrument: Hydrothermal synthesis reactor, electric balance, Brookfield rotary viscometer, incubator, electric blender, PH meter, measuring cylinder, beaker and so on.

4.1. The influence of coagulant aid HPAM on the gel system

Main agent content is selected 6 wt. %, the content of cross-linking agent I is 2.2 wt. %, the content of cross-linking agent II 1.5 wt. %, Investigation into the effects of the content of HPAM on the gelling properties of the gel system.




Figure 1. The Influence of HPAM on the Gel System

As shown in figure 1, the content of HPAM is proportional to the initial viscosity of the solution, the viscosity increases with the content of HPAM increases, but the gelling time reduces. So, the content of HPAM is 0.03wt.%.

4.2. The Influence of the modified high temperature resistant main agent on the gel system

The content of HPAM is selected 0.03 wt. %, the content of cross-linking agent I is 2.2 wt. %, the content of cross-linking agent II 1.5 wt. %, Investigation into the effects of the content of high temperature resistant main agent on the gelling properties of the gel system.

As shown in figure 2, the content of the main agent is proportional to the gelling viscosity, but inversely proportional to the gelling time, When the content of the

main agent is 6%, gelling time is the longest, the content of the main agent is between 6% and 10%, gelling viscosity change little. So, the content of the main agent is 6%.




Figure 2. The Influence of the Content of Main Agent on the Gelling Time and the Gelling Viscosity

4.3. The influence of the cross-linking agent on the gel system

Main agent content is selected 6 wt. %, the content of HPAM is 0.03 wt. %, the content of cross-linking agent II 1.5 wt. %. Investigation into the effects of the content of cross-linking agent I on the gelling properties of the gel system.




Figure 3. The Influence of the Content of Cross-linking Agent I on the Gelling Time and the Gelling Viscosity

The content cross-linking agent I is 2.2%, the mole ratio of cross-linking agent and cross-linking agent II is 2:5, the gelling viscosity of the System is the largest, when the content of cross-linking agent increase, the viscosity decrease; The gelling time of the cross-linking agent I content within 1.65% ~ 3.85% reduce with the increase of the content of cross-linking agent. So, the content of cross-linking agent I is 2.2%.

4.4. The influence of the cross-linking agent II on the gel system

Main agent content is selected 6 wt. %, the content of HPAM is 0.03 wt. %, the content of cross-linking agent I 2.2 wt. %. Investigation into the effects of the content of

cross-linking agent II on the gelling properties of the gel system.




Figure 4. The Influence of the Content of Cross-linking Agent II on the Gelling Time and the Gelling Viscosity

The content of cross-linking agent II is proportional to the gelling viscosity, is inversely proportional to the gelling time, When the content of cross-linking agent II is more than 1.8%, the final gel is semi-solid state, the gel is strength and the gel time is less than 4 hours, gelling time is short.

At last, through the experiment of ratio optimization, the formula is 0.03% coagulant aid 2.2% cross-linking agent I + 1.8% cross-linking II + 6% high efficient main agent.

5. The Optimization Experiment PF Compounded System

Drugs: Sodium carboxy methyl cellulose(CMC), graphite particle, Coagulant aid, high temperature resistant main agent, cross-linking agent I, cross-linking agent II. Instrument: tranquil flow pump, blender, PH meter, the sand filling tube, incubator, some pipelines, some the valves and four-ways, beaker, glass rod.

The content of suspending agent: Experiments are aim to explore the suspension ability of the suspending agent to graphite particles, By changing the content of suspending agent for suspension rate as the evaluation standard of the suspension ability[5,6], the computation formula of the rate of suspension is as follows:

$$Q = (h_1 - h_2) / h_1 \tag{1}$$

Where :Q is the rate of suspension, ml/ml ; h1 is the original particle volume of the suspension, ml ; h2 is the water which is separated out of the suspension after sit 48 hours, ml.

The results of the experimental show that when the content of CMC is 0.5%, the suspension performance is good, After 48 hours it almost won't appear the settlement, when it is 25 °C, the viscosity is the 61.4 mPa.s, When the content of the graphite particles is 2%, the liquidity and dispersion performance are good, it has not the phenomena of water separating. So, the content of CMC is 0.5% at last.

The content of the new inorganic particles: By measuring the plugging rate of sand filling tube of compounded system under different content of inorganic particle and the plugging rate which is scoured by 30 pv steam as the standard to screen and optimize the content of inorganic particles in experiment.




Figure 5. The Content of new Inorganic Particle

As shown in figure 5, with the content of the particle increasing, plugging rate increases, plugging rate is more than 98.4%, When the content of the graphite is more than 2%, it is difficult to injection. The experiments of scouring resistance show : After scouring, with the increasing of the content of particles, the plugging rate reduce until leveled off. When the content of the particle is 0.7%, the curve appears inflection point. So the choice of the content of particles of compounded systems is 0.7%.

6. Static Performance Evaluati-n of Plugging Agents System

6.1. The influence of temperature on the gel properties

Set the temperature 160 °C, 180 °C, 200 °C, 240 °C, 280 °C, examine the impact of temperature on the gel properties(Table1).

Experiment results show that the gelling viscosity of the profile control agent system is more than 43.2 ×104mPa.s in the range of the simulated formation temperature, it can meet the needs of the plugging, the system has the advantage of high efficiency and the wide range of gelling temperature[7].

Table 1. The Influence of Temperature on Gelling Time and Viscosity

T/°C	160	180	200	240	280
gelling viscosity /mPa.s×104	43.2	125	200	135	200

6.2. The influence of PH value on gel properties

Set reaction temperature 200 °C, studying the effect of PH on gel properties(Table 2).

Experiments show that when PH is between 6 ~ 8, it has a little influence on gelling viscosity and gelling time, When the PH > 9 or PH < 5, the change of the gelling

viscosity is irregular over time, it cannot gel. Salinity has little influence on the performance of gel, therefore it is no longer here.

Table 2. The Influence of PH Value on Gelling Time and Viscosity

No.	PH	gelling time /h	gelling viscosity / mPa·s
1	6	6	2×106
2	7	5	2×106
3	8	7	1.57×106
4	9	—	No gelling

7. Dynamic Evaluation Test

7.1. Plugging ratio and residual resistance factor

Table 3. Result of Plugging Ratio and Residual Resistance Factor

Type	T (°C)	perm-plug method (Md)	Water permeability measurement (mD)		plugging ratio (%)	RRF
			before the seal	After the seal		
Gel	200	3435	680	14	97.94	48.57
	240	2830	670	12	98.21	55.83
	280	3611	801	26	96.75	30.81
Compound	200	3015	988	9	99.08	109.8
	240	3244	912	8	99.12	114
	280	3158	945	9	99.05	105

7.2. Scouring Resistance and Thermal stability

Scouring resistance

Injecting 30PV steam into the sand filling tube at the rate of 3 ml/min after sealed, Simulation environment temperature is 280°C, back pressure is 2.4MPa. Measuring water phase permeability after scoured, compare the plugging ratio before and after scoured(Table4). Com-

Turning the sand filling tube into vacuum, water-saturated. Then, measured the pore volume and the permeability before plugging, displace 3PV profile control agent into sand filling tube at a constant speed of 1 ml/min, sealed, and put it into thermostat at the temperature of 200°C for 12 hours until gelatinized, Comparing the plugging ratio and residual resistance factor of gel system and composite systemat different temperature(Table3).

Compounded system has better sealing ability than gel system, plugging rate achieves above 99%, Plugging effect is little changed with temperature.

pared with gel system, after 30PV high speed and high temperature steam flushing, plugging ratio of compounded system only drop in 0.35%. It means that compounded system has excellent perform in terms of scouring resistance and it can extend the period of validity.

Table 4. The Compared Result of Scouring Test

Injection Medium	perm-plug method (mD)	Water permeability measurement (mD)				plugging ratio (%)		
		before the seal	After the seal	15PV	30PV	After the seal	15PV	30PV
Gel	3435	680	14	71	336	97.94	89.56	50.59
Composite	3224	912	8	9	11	99.12	99.01	98.78

thermal stability

Under the condition of high temperature, most polymers are prone to degrade to hydration. In the steam flooding, retention ability of profile control agent can be measured by thermal stability through the curve of time-plugging ratio. The formation temperature of simulated is 280°C. By plugging rate change with time to study thermal stability[8].

At the temperature of 280°C, plugging ratio is still above 98.4% after 10 days and gradually to be steady. Particles and gel support each other to approve excellent thermal stability. The compounded profile control agent still has good performance after gel system degrade.




Figure 6. Result of Gel and Compounded Thermal Stability

8. Conclusions

Compounded with the new high-temperature -resistant inorganic materials and the modified high-temperature-resistant gel system, New thermal recovery high-

temperature-resistant composite profile control agent is provided through simple preparation process, excellent performance and widely sources of materials;

The gel system contained in the compounded system has a wide reaction temperature, it withstand at least 280°C, pH which is suitable is range from 6 to 8. The compounded control agent has good performance in injection, scouring resistance and thermal stability. Plugging rate is more than 99%;

Compounded system has high plugging rate with the less amount of particle, Gel can be degraded by the steam washing, the lubricity of particles make it harmless to pump during the injection and production;

Using the double-fluid method to inject under the condition of low pressure and low emissions. The new thermal recovery high-temperature-resistant compounded profile control agent owes a high practical value and a wide application prospect.

References

- [1] liu, Q. H, Pei, H. H, Wang, Y., Jiang, P., Wang, Z. W., & Li, H. T. (2013). Research Progress of Heat-Resistant Profile Control Agent. *Oilfield Chemistry*, 1, 036.
- [2] Tong, S., & Liu, Y. J. (2012). The Application and Prospect of Profile Control and Plugging Agent with High Temperature Resistant in Steam Thermal Recovery. *Sino-Global Energy*, 17(1), 47-50.
- [3] Song, C. H. Zhao, C. X., Wu, H. X., Han, X. W. Liu, Y. J., & Han, H. J. (2010). Technological research on BQ 10block steam drive profile control channeling block. *Petroleum Geology and Engineering*, (1), 101-103.
- [4] Duan, Y. Z. (2010). Study on Multisystem Combined with Chemical Profile Control;l and Displacement for Heavy oil Thermal Recovery (Doctoral dissertation, China University of Petroleum).
- [5] Zhang, W. X. (2013). Comprehensive regulation technique research and application of steam flooding in Qi 40 Block (Master's thesis, Northeast Petroleum University).
- [6] Zhang, X. (2011). Research on Technologies and Its Mechanism for Improving Efficiency of Steam Flooding in Medium Depth Heavy Oil Reservoir (Doctoral dissertation, Northeast Petroleum University).
- [7] Eson, R. L., & Cooke, R. W. (1992, January). A successful high-temperature gel system to reduce steam channeling. In *SPE Annual Technical Conference and Exhibition*. Society of Petroleum Engineers.
- [8] Hunter, B. L., Buell, R. S., & Abate, T. A. (1992, January). Application of a polymer gel system to control steam breakthrough and channeling. In *SPE Western Regional Meeting*. Society of Petroleum Engineers.